



TDS of AC-318F Single Side Butyl Tape with Non-woven Fabric Backing

ITEM	CONDITION	STANDNRD	RESULT	STANDARD	
CONTINUAL FORCE Min (steel ball)	23°C	≥8	13.3	GB/T 4851-98	
CLARITY HUMIDITY g/m ² 24H	0.3mpa,24h	≤3	0.6	GB/T 12952-03	
LOW TEMPERATURE FLEXIBILITY	-40°C	NO CRACKLE ON SURFACE	NO CRACKLE ON SURFACE	ASTM C731	
APPLICATION TEMPERATURE		-40 to 90°C			
UV RESISTANCE	U.V LIGHT FOR 2000H	NO CHANGE IN COLOR OR HARDNESS. NO CRACKING, KEEP ADHESION	NO CHANGE IN COLOR OR HARDNESS. NO CRACKING, KEEP ADHESION	ASTM G-53	
TAKING- OUT FORCE (N/CM)	GLASS PANEL	23°C 300mm/min	≥10	15.8	ASTMD3330-02
	CEMENT SLAB			17.3	
	Al-CASE			14.8	
	Cu-CASE			14.4	
	STAINLESS STEEL SLAB			16.3	
	PVC SLAB			15.7	

NOTE: THE USE LIFE OF THIS PRODUCT IS MORE THAN 20 YEARS.

