

DESCRIPTION

PENEPLUG® is a rapid setting, integral crystalline cementitious waterstop designed to stop active water leaks and moisture ingress.

RECOMMENDED FOR

PENEPLUG® can be used internally or externally as a waterproof plugging mortar or where rapid setting and early strength gain is required.

- ▶ Plugging/stopping active water leaks
- ▶ Sealing of leaking joints, form tie holes or cracks

PENEPLUG® can be used on the following substrates:

- ▶ Concrete
- ▶ Masonry
- ▶ Earthenware
- ▶ Stone

ADVANTAGES

- ▶ Stops water flow
- ▶ Sets in approximately 30 seconds after mixing
- ▶ Durable
- ▶ Can be used underwater
- ▶ Can be mixed with water or used dry
- ▶ Easy to apply
- ▶ Packaged in easy to use, re-sealable containers

DIRECTIONS FOR USE

Surface Preparation: The substrate must be clean, sound and free of any surface contamination, such as oils, coatings, paints, dirt, etc. Leaking areas must be cut back to sound material, leaving an appropriate chase for receiving PENEPLUG®.

Mixing: Setting time is dependent largely on the amount of mixing water used. Standard mix ratio at 68°F (20°C) is 2.5 lb (1 kg) PENEPLUG® and approximately 1 cup (0.25 l) of water. PENEPLUG® must be added to the water and mixed quickly. The mix should have a dry pack (dry earth) consistency, holding a shape when squeezed in your hand but easily crumbled when pressed with fingers. Mixing time is about 15 seconds with setting occurring about 30 seconds later. In cold weather, use lukewarm water. In higher temperatures, use cold water.

Application:

To avoid waste, only small quantities of PENEPLUG® should be mixed.

After mixing, apply PENEPLUG® to the appropriate area immediately. Material should be formed into a wedge and forced into the leak. This can be accomplished with the use of a block of wood and hammer. Work the plug well into the area and then, applying as much pressure as possible, hold firmly in place for about 30 seconds or until set.

After the leak has stopped, fill the remaining void to the surface with PENECRETE MORTAR™.

Remove excess material.

After lightly pre-wetting, apply a final coat of PENETRON® to the repaired area.

In certain circumstances PENEPLUG® may be applied as a dry powder. After preparing the surface as described above, place and hold the powder directly over the leak for 30-60 seconds.

PACKAGING

This product can be purchased in 40 lb (18 kg) bags or 55 lb (25 kg) pails.

STORAGE / SHELF LIFE

PENEPLUG® should be stored dry at a minimum temperature of 45°F (7°C). When properly stored in a dry cool place in unopened and undamaged original packaging, shelf life is 12 months.

SAFE HANDLING INFORMATION

PENEPLUG® contains cement which is alkaline. Will irritate eyes and skin and may cause skin sensitization. Wear appropriate eye, skin and breathing protection when using this product. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. For further information please refer to Material Safety Data Sheet. KEEP OUT OF REACH OF CHILDREN.



1085-CPD-0040
EN 1504-3

ICS Penetron International Ltd.
601 South Tenth Street, Unit 300
Allentown, PA 18103

08
PENEPLUG

for structural and non-structural repair CC mortar

Compressive strength: Class R3 (≥ 25 MPa)

Chloride content: < 0,05 % by mass
Adhesive bond: NPD

Restrained shrinkage, expanding: NPD
Elastic modulus: NPD

Thermal compatibility (Part I): ≥0,8 MPa

Corrosion behaviour: deemed to have
no corrosive effect

Reaction to fire: NPD

Dangerous substances: NPD

WARRANTY

ICS PENETRON INTERNATIONAL LTD. warrants that the products manufactured by it shall be free from material defects and will conform to formulation standards and contain all components in their proper proportion. Should any of the products be proven defective, the liability to ICS PENETRON INTERNATIONAL LTD. shall be limited to replacement of the material proven to be defective and shall in no case be liable otherwise or for incidental or consequential damages. ICS PENETRON INTERNATIONAL LTD. MAKES NO WARRANTY AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE AND THIS WARRANTY IS IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED. User shall determine the suitability of the product for his intended use and assume all risks and liability in connection therewith.