

FastFloor® Chemical Resistance

Results based on dry film thickness of 6 mils.

Pigmented Chemical Resistance	1 hr	4 hr	24 hr
Brake Fluid	No Effect	No Effect	No Effect
Gasoline	No Effect	No Effect	No Effect
Skydrol	No Effect	No Effect	No Effect
Sulfuric Acid (50%)	Slight Soften	Slight Soften	Blister
Ammonium Hydroxide (50%)	No Effect	No Effect	No Effect
Anti-freeze	No Effect	No Effect	No Effect
IPA	No Effect	No Effect	Slight Soften
Motor Oil	No Effect	No Effect	No Effect
Tranmission Fluid	No Effect	No Effect	No Effect
Dissolved Rock Salt	No Effect	No Effect	No Effect

Clear Chemical Resistance	1 hr	4 hr	24 hr
Brake Fluid	No Effect	No Effect	No Effect
Gasoline	No Effect	No Effect	No Effect
Skydrol	No Effect	No Effect	No Effect
Sulfuric Acid (50%)	Slight Soften	Slight Soften	Soften
Ammonium Hydroxide (50%)	No Effect	No Effect	No Effect
Anti-freeze	No Effect	No Effect	No Effect
IPA	No Effect	No Effect	Slightly Soften
Motor Oil	No Effect	No Effect	No Effect
Tranmission Fluid	No Effect	No Effect	No Effect
Dissolved Rock Salt	No Effect	No Effect	No Effect