



Leakmaster

1. Technical data

1.1 General:

- composition: Polyurethane,
- Appearance: grey paste
- specific gravity: 1,3 kg/dm³
- slump: max. 3 mm (at 23°C)
- tack free time: within 8 hours (at 23°C, 60% relative humidity)

1.2 After hardening:

- hardness: 35
- tensile strength: 30 kg/cm²
- elongation: 1.250%
- tear strength: 10 kg/cm
- swelling: 200% after 10 days of full immersion min. 350% at 10°C

2. Adhesion properties

	Steel	Aluminium	Mortar
50% modulus (kg/cm ²)	4,5	6,5	6,5
Max. tensile strength (kg/cm ²)	7,0	12,2	11,1
Elongation at break (%)	330	580	570

3. Volume

320 ml/cartridge

4. Packaging

24 cartridges/carton

-1-

Leakmaster

With you every step of the way

