

DESCRIPTION: RhinoCoat™ GP (General Purpose) an extremely tough workhorse epoxy with excellent chemical resistance. A two component, solid colour, high solids, silicone free, low viscosity, self-priming, glossy epoxy resin available in wide color range. Typically installed as a seamless, high build, smooth coating for light to medium duty traffic areas. This general service epoxy coating demonstrates good mechanical and chemical resistance.

TYPICAL USES: RhinoCoat GP is often used as a primer, binder and top coat for a wide range of coating applications. Often used in Aircraft hangers, Retail stores, Light to Medium duty manufacturing, commercial and industrial facilities.

FEATURES & BENEFITS:

- Good chemical resistance
- Low viscosity
- Nice gloss appearance
- Does not support bacteria growth
- Easy to clean & maintain
- Durable, impermeable and seamless
- Neutral Odour
- Excellent adhesion
- Good mechanical resistance
- Cost effective

CHEMICAL PROPERTIES:	Result
Viscosity, cps	525-675
Solids by Volume/Weight	100%
Volatile Organic Compounds	0 lbs/gal
Mix Ratio, parts per volume	2A :1B
Pot Life, minutes	15 - 30 minutes
Recoat, max	12 - 24 hrs
Dry to Touch @ 70°F (21°C)	6 hrs
Walk on Time (light foot traffic)	24 hrs
Return to Service Time (vehicle traffic)	3 days
Full Cure	7 days
Coverage Rate per Gallon	100 – 400 sqft (2.0 – 9.8 sm/l)
Recommended Application Temperature	41° – 86°F (5° – 30°C)
Odor	Low
Flash Point, closed cup	340°F (170°C)
Color	Clear with Universal Color Packs
Shelf Life - unopened containers	12 months

RHINOCOAT™ GP (continued):

PHYSICAL PROPERTIES:	Test	Result
Hardness (Shore D)	ASTM D-2240	525-675
Tensile Strength (psi)	ASTM D-638	7,500
Elongation (%)	ASTM D-638	2 - 5 %
HDT	ASTM D-648-264	120°F
Compressive Strength (psi)	ASTM D-695	10,300
Water Absorption, gain in 24 hrs (%)	ASTM D-695	<0.1
Flexural Strength (psi)	ASTM C-790	7,000
Bond Strength	Greater than cohesive strength of 3,000 psi concrete, <220 pai	
Temperature Resistance	Continuous Exposure	Up to 150 F

SURFACE PREPARATION: The surface to be coated should be thoroughly clean; free of any contaminants such as oil, grease or incompatible coating materials. Abrasive blasting or power scrubbing with detergent, acid washing, neutralizing and pressure washing are common surface preparation methods.

MIXING INSTRUCTIONS: The mixing ratio for RhinoCoat™ GP is 2 parts A (resin) to 1 part B (hardener). Mix thoroughly for 3 minutes using a drill motor and mixing paddle or for small quantities (1 ½ gal./ 5.7 liters) a stir stick can be used. Scrape the sides and bottom of the container while mixing. After mixing, allow a 3 minute induction period then mix again for approximately 15 seconds. Immediately pour the entire bucket in a thin row on the floor and begin spreading. If it sits in the bucket too long, it may set up prematurely. Mix only the amount of material that can be used in a 15 – 20 minute time period.

APPLICATION METHODS: Air or airless spray (heaters and plural component equipment not required), roller, squeegee, brush (small areas), “chopped” and “hand lay-up” method.

NOT RECOMMENDED FOR: Do not apply to concrete less than 28 days old.

SUBSTRATES: Concrete and steel

COLOR OPTIONS: Clear and 16 Universal Color options (see RhinoFlooring Color Chart)

HOW SUPPLIED: RhinoCoat™ GP is packaged in 1.5 gallon and 3 gallon kits.

SLIP/FALL PRECAUTIONS: Rhino Linings recommends using slip resistant granules in all outdoor applications where the epoxies and urethanes will be used as a topcoat sealer and on indoor applications that may be exposed to water, oil or other spills that may cause a slippery environment. Aluminum oxide granules #80 grit or courser may be broadcast into the prime coat to achieve the amount of slip resistance desired. It is the end user’s responsibility to determine the suitability of a coating for their particular application. Rhino Linings or its sales agents will not be responsible for injury incurred in a slip/fall accident.

SAFETY PRECAUTIONS: Health Considerations: Consult the Rhino Linings® Safety Data Sheets (SDS) Chemical systems require the use of proper safety equipment and procedures. Please follow the Rhino Linings® product SDS and Safety Manual for detailed information and handling guidelines.

For Your Protection: The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions made concerning the products and their uses, applications, storage and handling are only the opinion of Rhino Linings Corporation. Users should conduct their own tests to determine the suitability of these products for their own particular purposes and of the storage and handling methods herein suggested. The toxicity and risk characteristics of products made by Rhino Linings Corporation will necessarily differ from the toxicity and risk characteristics developed when such products are used with other materials during a manufacturing process. The resulting risk characteristics should be determined and made known to ultimate end-users and processors. Because of numerous factors affecting results, **Rhino Linings Corporation makes no warranty of any kind, express or implied**, other than that the material conforms to its applicable current Standard Specifications. Rhino Linings Corporation hereby disclaims any and all other warranties, including but not limited to those of merchantability or fitness for a particular purpose. No statements made herein may be construed as a representation or warranty. The liability of Rhino Linings Corporation for any claims arising from or sounding in breach of warranty, negligence, strict liability, or otherwise shall be limited to the purchase price of the material.

©2018 Rhino Linings Corporation. All rights reserved.



Rhino Linings Corporation
 9747 Businesspark Avenue, San Diego, CA 92131
 858-450-0441 • Fax 858-450-6881
 1-800-422-2603
 www.rhinolinings.com